

Certificate of Calibration



Equipment calibration was performed for:



Thursday, February 20, 2025

Calibration performed by:

	Calibration Summary											
Applied Force	Average Microstrain (μe)	Max Bending (%)	Max Bending Strain (μe)	ASTM E-1012 Tolerance	Uncertainty (μe)	Pass/Fail						
6000-lbf	1019.0	7.98	N/A	≤10% Bending	15	PASS						
12000-lbf	2058.1	4.57	N/A	≤10% Bending	26	PASS						
18000-lbf	3095.6	3.33	N/A	≤10% Bending	36	PASS						

ALIGNMENT VERIFICATION INFORMATION

ASTM Round Specimen, .500" Dia, 1" Shanks, Inconel 718 Stainless material - Serial# 10408920

ALIGNMENT TRANSDUCER INFORMATION	DESCRIPTION: LOAD TRAIN AND GRIPPING METHOD
Instrumentation consists of 12 foil type strain gauges adhesively fastened to the specimen. The gauges are arranged	Load train consists of the following in order from top: Castle nut atop threaded rod on top of crosshead, threaded
at four positions around the specimen on each plane. Strain measuring device has a sensitivity of 0.1 micro strain,	rod through crosshead, alignment fixture, load cell, upper hydraulic grip, axial alignment specimen, lower hydraulic
and relative accuracy of +/- 1.09 · 1.0 micro strain.	grip mounted to base.

* Decision Rule: Simple Acceptance Rule was used - readings fall within tolerance. Measurement uncertainty is stated, but not used to determine pass/fail status. TUR is > 4:1, unless stated.

Cal-Rite has calibrated the testing equipment described above in accordance with the latest applicable specifications (ISO/IEC 17025, ANSI Z-540-1 and 10-CFR-21). All calibration measurements are traceable to the International System of Units (SI) through NIST. The results of this calibration apply only to the unit that was calibrated. The uncertainty of the calibration process was estimated approximately at the 95% confidence level (k=2).

Service Notes

Alignment performed IAW ASTM E1012 Class 10. All readings within tolerance.

AS A MUTUAL PROTECTION TO THE PURCHASER, THE PUBLIC, AND OURSELVES, ALL CAL-RITE CALIBRATION REPORTS ARE SUBMITTED AS THE CONFIDENTIAL PROPERTY OF THE PURCHASER, AND ANY AUTHORIZATION FOR PUBLICATION OF STATEMENTS, CONCLUSIONS, OR EXTRACTIONS FROM OR REGARDING OUR REPORTS IS RESERVED PENDING OUR PRIOR WRITTEN APPROVAL.



Axial Alignment Verification



	Instrument Profile													
Manufacturer:	TensileMIll	Machine Serial No.:	VTS240720	Max Force:	18,000 lbf	Temp/Humidity:	72.6°F/42.6%RH	Date:	2/20/2025					
Model/Type:	EML 305D	Load Cell Serial No.:	34037757	Direction:	Tension	Verification Type:	Type 2	Next Due:	As Required					
Asset ID#:	N/A	Alignment Fixture Serial No.:	Not Marked	Specimen Type:	Round	Software Version:	MaxTest 7.79	Class:	10%					

Calibration Results

Strain Gage Configuration



Run 1											
Ro	tation - (0°	Applied Force 1bf								
Free	Grip	Gage	6000	12000	18000						
0	12	$\mathbf{e_1}$	1046	2111	3167						
0	4	\mathbf{e}_2	988	2014	3035						
0	-9	\mathbf{e}_3	993	2009	3027						
0	7	e ₄	1056	2114	3171						
Load	Load	e _{avg}	1021	2062	3100						
Max	Bending S	train	43	71	98						
Erre	or % Ben	ding	4.2%	3.5%	3.1%						

Run 2											
Rot	ation - 1	80°	Applied Force 1bf								
Free	Grip	Gage	6000	12000	18000						
0	4	e ₁	941	1965	2994						
0	-11	\mathbf{e}_2	993	2058	3118						
0	9	\mathbf{e}_3	1097	2153	3198						
0	14	e ₄	1051	2069	3088						
Load	Load	e _{avg}	1021	2061	3100						
Max	Bending S	train	83	94	103						
Erre	or % Ben	ding	8.2%	4.6%	3.3%						

		Ku	n s									
Rotation - 0°			Appli	Applied Force 1bf								
Free	Grip	Gage	6000	12000	18000	Upper Strain						
0	18	$\mathbf{e_1}$	1071	2132	3183		10.0% ¬		pper strain			
0	12	\mathbf{e}_2	1086	2104	3124	ų	8.0% - 6.0% -		_			
0	-11	\mathbf{e}_3	969	1989	3009		6.0% -			_	6000	
0	-7	e ₄	959	2025	3081		% 4.0% - E 3.0%				12000	
Load	Load	e _{avg}	1021	2063	3099		2.0% 0.0%				■ 18000	
Max	Bending S	Strain	81	82	90			RUN1	RUN2	RUN3		
Err	or % Ben	ding	8.0%	4.0%	2.9%	% APPLIED FORCE						
									-			

IV	IIDD	LE
	7	
8	5	6
	IAN	IE .

Free	Grip	Gage	6000	12000	18000
0	4	e ₁	1019	2058	3093
0	2	\mathbf{e}_2	1016	2055	3090
0	7	\mathbf{e}_3	1024	2070	3112
0	6	e_4	1014	2046	3092
Load	Load	eavg	1018	2057	3097
Max	Bending S	Strain	3	8	10
Err	or % Ben	ding	0.3%	0.4%	0.3%

Free	Grip	Gage	6000	12000	18000
0	-17	$\mathbf{e_1}$	974	2019	3062
0	3	\mathbf{e}_2	1000	2047	3090
0	15	\mathbf{e}_3	1069	2108	3143
0	11	e ₄	1032	2058	3082
Load	Load	e _{avg}	1019	2058	3094
Max Bending Strain			50	45	41
Error % Bending			4.9%	2.2%	1.3%


ee	Grip	Gage	6000	12000	18000	Middle Strain	
)	11	$\mathbf{e_1}$	1042	2081	3116	10.0%	
)	4	\mathbf{e}_2	1074	2108	3138	8.0%	
)	-5	\mathbf{e}_3	1003	2047	3088		= 6000
)	1	e ₄	960	1998	3032	% 4.0% E 2.0%	12000
ad	Load	e _{avg}	1020	2059	3094	2.0% LB 2.0%	■ 18000
Max Bending Strain		60	58	55	RUN1 RUN2 RUN3		
Error % Bending		5.9%	2.8%	1.8%	APPLIED FORCE		

LC	owi	ER
12	11 9	10
Р	LAN	IE

Free	Grip	Gage	6000	12000	18000
0	6	e ₁	994	2009	3025
0	16	\mathbf{e}_2	1038	2083	3130
0	-9	e ₃	1039	2099	3152
0	-13	e ₄	997	2028	3090
Load	Load	e _{avg}	1017	2055	3099
Max	Bending S	Strain	30	53	67
Err	or % Ben	ding	3.0%	2.6%	2.1%

ı	Free	Grip	Gage	6000	12000	18000
	0	-1	e ₁	1009	2072	3128
۱	0	-3	\mathbf{e}_2	1000	2024	3047
	0	4	\mathbf{e}_3	1025	2035	3049
ı	0	7	e ₄	1035	2085	3133
l	Load	Load Load e _{avg}		1017	2054	3089
	Max Bending Strain			19	36	58
	Error % Bending			1.9%	1.7%	1.9%

Free	Grip	Gage	6000	12000	18000
0	5	e ₁	1015	2035	3054
0	16	\mathbf{e}_2	1059	2106	3145
0	1	\mathbf{e}_3	1019	2073	3121
0	-9	e ₄	976	2003	3035
Load	Load Load e _{avg}		1017	2054	3089
Max	Max Bending Strain			55	64
Error % Bending			4.1%	2.7%	2.1%



Calibrating Apparatus Used

Asset Number	Manufacturer:	Model	Serial Number	Calibration Date	Calibration Due	Calibrated By	
AS3	MTS	709.20E	1DE61E7	5/4/2024	5/4/2025	CRC	

PROCEDURE: CR113 rev 7 SPECIFICATION: ASTM E1012-19

QMS REVISION: 3.01

GIL GUTIERREZ
Service Technician

Service Order #:	N/A

Purchase Order #: N/A

AS A MUTUAL PROTECTION TO THE PURCHASER, THE PUBLIC, AND OURSELVES, ALL CAL-RITE CALIBRATION REPORTS ARE SUBMITTED AS THE CONFIDENTIAL PROPERTY OF THE PURCHASER, AND ANY AUTHORIZATION FOR PUBLICATION OF STATEMENTS, CONCLUSIONS, OR EXTRACTIONS FROM OR REGARDING OUR REPORTS IS RESERVED PENDING OUR PRIOR WRITTEN APPROVAL.

AL 2-22 PAGE 2 OF 2